



شركة بريما فوم للصناعات المتطورة

Prima Foam For Developed Industries

XPS

Properties	Unit	Standard	ECO	ECO+	ECO++
Density	kg\m3	ASTM1622	30-31	32-33	36-37
Compression Strength	kpa	ASTM1621	280	300	420
Water Absorption	% (v\ v)	ASTMC272	0.3	0.2	0.1
Thermal Conductivity	W\mk	ASTMCS18	0.028	0.025	0.020
Flammability	Class	DIN4102	B2	B2	B2
Dimensional Stability	%	-----	s2.0	s2.0	s2.0

Properties	Dimension
Length	2400 / 1800 / 1200
Width	610
Thickness	100 / 90 / 80 / 70 / 60 / 50 / 40 / 30 / 25 / 20
Edge	Shiplap or square